



R = *i*-butyl



FW 931.63

D_4^{20} 1.14

n_D^{20} 1.47

Solvent Solubility

THF chloroform, hexane

Solvent Insolubility

acetonitrile

Resin Solubility

aliphatic and aromatic resins

Appearance

white powder

Uses

grafting agent, chain terminator,
improved toughness

Refrigerate

CAS [444315-17-7]

100g/\$325

50g/\$195

25g/\$145